

PRECISION TESTING LABORATORIES

313 Hill Avenue; Nashville, TN 37210-4711
Phone 615-254-3401 Fax 615-254-3488
www.precisiontesting.com

Laboratory Report No. 74886
19-Sep-06

Mr. Mike Cole
Royal Carolina Corp.
7305 Old Friendly Road
Greensboro, NC 27410

Item: One (1) sample identified as:
1) Green

Purpose: Flammability, NFPA 701-2004, Test I

Test	Specimen Results									
------	------------------	--	--	--	--	--	--	--	--	--

Flammability, NFPA-701-2004
Test I

<u>% Weight Loss</u>	26.1	33.3	31.5	33.7	30.7	27.7	29.3	36.9	18.0	31.7
<u>Residue Burn (seconds)</u>	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
<u>Standard Deviation</u>	5.20									
<u>3 Standard Deviations</u>	15.59									
<u>Retest Required</u>	No									

Retest Requirement

9.1.4 When the percent mass loss of any individual specimen exceeds the mean value plus 3 standard deviations, the test shall be repeated on another sample of 10 specimens.

Flame Propagation Performance Requirement

- 10.1.1.1 Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens.
- 10.1.1.2 The average weight loss of the 10 specimens in a sample shall be 40 percent or less.
- 10.1.1.3 No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
- 10.1.1.4 When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.

Sample conforms with NFPA 701, Test I requirements.

sg

Average

29.9

0.0